













Atacid Colours on Nylon fibre

Atacid (o.w.f)	100% Nylon	C.I. Acid	Solubility 80oC(g/l)	Type	Light Fastness	Washing Fastness	Rubbing Fastness
Yellow 5GW (1.0%)		Y 127	70	M	6	4-5	5
Tartrazine (1.0%)		Y 23	70	M	3	4-5	5
Yellow M-GR (1.0%)		Y 42	35	M	3	4-5	5
Orange AGT (1.0%)		Or 116	40	M	5	5	5
Red GS (1.0%)		R 151	40	HL	5-6	2-3	4
Carmine 4BA (1.0%)		V 12	50	L	5-6	5	5
Violet FBL (1.0%)		V 48	100	M	5-6	5	5
Rubine 5BLF (1.0%)		R 299	50	M	5-6	4-5	4-5
Red Brown MV (1.0%)		R 119	40	M	6-7	3	5
Brown TM (1.0%)		Mix	30	M	5	3	4-5
Sky Blue R (1.0%)		B 62	50	L	5-6	3-4	3-4
Turq. Blue 5G (1.0%)		B 185	100	M	1-2	4	5
Cyanine M-5R (1.0%)		B 113	70	M	6	3	5
Black LDN (2.0%)		Bk 172	80	MC	5-6	3-4	4
Black M-SRL (2.0%)		Bk 194	75	M	5-6	3-4	4